

**Product**

**GLF0265C**

**Appearance**



**Specification**

<b>Dielectric Constant</b>	2.65±0.05	@10GHz
<b>Dielectric Loss Tangent</b>	0.0018	@10GHz
<b>PIMD(dBc)</b>	161	20Watts@1800MHz
<b>CTE(Z:ppm/°C)</b>	65	-50°C~288°C
<b>Thermal Conductivity</b>	0.39	@80°C
<b>Tg (°C)</b>	>300	---
<b>Moisture Absorption</b>	0.05%	D23/24
<b>Peel Strength (N/mm)</b>	2.5	After thermal stress
<b>Flammability</b>	V-0	---

**Dimension**

**Panel size (inch): 18\*12/18\*24/36\*48**

**Thickness (mil): 10/20/30/40/50/60/100/400**

**The thickness of the copper foil (um): 35/17/70**